

LAVA (DALIAN) INTERNATIONAL TRADE CO.,LTD

No.155,Shandong Road,Dalian,116031,China.Tel/Fax:(86)0411-39563205

Website: www.lavadl.com Mail to: info@lavadl.com

Main Products Catalog



Fluorspar Dry Powder

Spec.	98-97% Dry Powder	96-95% Dry Powder	93-90% Dry Powder	90-88% Dry Powder	85-80% Dry Powder
CaF ₂	≥97%	≥95%	≥90%	≥88%	≥80%
SiO ₂	≤0.8%	≤1.5%	≤2.5%	≤3%	≤4%
CaCO ₃	≤1.0%	≤1.0%	≤1.5%	≤2%	≤2.5%
P	≤0.03%	≤0.03%	≤0.05%	≤0.05%	≤0.08%
Moisture	≤1%				

Fluorspar Wet Powder

Spec.	98-97% Dry Powder	96-95% Dry Powder	93-90% Dry Powder	90-88% Dry Powder	85-80% Dry Powder
CaF ₂	≥97%	≥95%	≥90%	≥88%	≥80%
SiO ₂	≤0.8%	≤1.5%	≤2.5%	≤3%	≤4%
CaCO ₃	≤0.8%	≤1.0%	≤1.5%	≤1.5%	≤2%
P	≤0.03%	≤0.03%	≤0.05%	≤0.05%	≤0.08%
Moisture	≤10%				



LAVA (DALIAN) INTERNATIONAL TRADE CO.,LTD

No.155,Shandong Road,Dalian,116031,China. Tel/Fax:(86)0411-39563205

Website: www.lavadl.com Mail to: info@lavadl.com

LAVA (DALIAN) INTERNATIONAL TRADE CO.,LTD

No.155,Shandong Road,Dalian,116031,China.Tel/Fax:(86)0411-39563205

Website: www.lavadl.com Mail to: info@lavadl.com

Fluorspar Ball

Spec.	93% Ball	90% Ball	85% Ball	80% Ball	75% Ball
CaF ₂	≥93%	≥90%	≥85%	≥80%	≥75%
SiO ₂	≤3%	≤4%	≤5%	≤8%	≤15%
CaCO ₃	≤1.0%	≤1.0%	≤1.5%	≤2%	≤2.5%
P	≤0.05%	≤0.05%	≤0.07%	≤0.08%	≤1.0%
Moisture	≤1%				
Size	10-45mm				

Fluorspar Lumps

Spec.	95% Lumps	90% Lumps	85% Lumps	80% Lumps	75% Lumps
CaF ₂	≥95%	≥90%	≥85%	≥80%	≥75%
SiO ₂	≤4%	≤7%	≤13%	≤17%	≤20%
CaCO ₃	≤1.5%	≤2%	≤2.5%	≤3%	≤3%
Size	10-100mm				

The Fluorite Lumps Quality Standards

Spec	Ultra-2 th grade	Ultra-1 th grade	1 th grade	2 th grade	3 th grade
CaF ₂ ≥%	98	97	95	90	85
SiO ₂ ≤%	0.8-1.3	1.5-2.5	1.8-4.5	3-9	5-14
S≤%	0.05	0.05	0	0.1	0.15
P≤%	0.03	0.05	0.06	0.06	0.06
Spec	4 th grade	5 th grade	6 th grade	7 th grade	
CaF ₂ ≥%	80	75	70	65	
SiO ₂ ≤%	10-18	18-23	23-28	25-32	
S≤%	0.2	0.2	0.25	0.3	
P≤%	0.08	0.08	0.08	0.08	



LAVA (DALIAN) INTERNATIONAL TRADE CO.,LTD

No.155,Shandong Road,Dalian,116031,China. Tel/Fax:(86)0411-39563205

Website: www.lavadl.com Mail to: info@lavadl.com